

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 070 736 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
24.01.2001 Bulletin 2001/04

(51) Int Cl.7: **C08J 5/18, C08L 23/10,
C08L 23/04, C08K 3/00**

(21) Application number: **99308650.3**

(22) Date of filing: **01.11.1999**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

- **Kim, Young Wook**
Yusung-ku, Taejon 305-390 (KR)
- **Kim, Tae Joon**
Yusung-ku Taejon 305-390 (KR)
- **Jo, Byoung Cheon**
Yusung-ku, Taejon 305-390 (KR)

(30) Priority: **23.07.1999 KR 9903004**

(71) Applicant: **SK Corporation**
Yongdungpo-ku, Seoul (KR)

(74) Representative: **Wilkinson, Stephen John**
Stevens, Hewlett & Perkins
1 St. Augustine's Place
Bristol BS1 4UD (GB)

(72) Inventors:
• **Lee, Young Keun**
Yusung-ku, Taejon 305-390 (KR)

(54) **Composition for air permeable film of high processability and permeability and production of air permeable film**

(57) Disclosed are a composition for an air-permeable film of high permeability and processability. The composition comprises 30 to 100 weight parts of a linear, low density polyethylene resin which ranges, in molecular weight distribution, from 7 to 20, 1 to 100 weight parts of a polypropylene resin, 1 to 30 weight parts of an ethylenepropylene copolymer, 5 to 30 weight parts of a polyolefin resin which has a melt index of 20 or high-

er, and 50 to 200 weight parts of an inorganic filler based on 100 weight parts of the total resins. It has advantages of assuring high permeability even at a low draw ratio, minimizing the unbalance in physical properties between the machine direction and the transverse direction of the drawn film, improving the tensile strength of the film, and preventing the physical property degradation due to the inorganic filler.

EP 1 070 736 A1

Description

TECHNICAL FIELD

5 [0001] The present invention relates, in general, to a composition for an air permeable film and, more particularly, to a composition which can be molded into an air-permeable film with superior processability, tensile strength and permeability. Also, the present invention is concerned with a method for producing such a film.

PRIOR ART

10 [0002] Many methods for producing air permeable or porous films are disclosed. Of them, the following process is known as being the most economically favorable and now commercialized: a mixture of a polyolefin resin and an inorganic filler is formed into a film which is then mono- or bi-axially drawn to subject the resin and the filler to interfacial separation, thus forming fine pores.

15 [0003] Prior arts directed to the production of air permeable films taking advantage of inorganic fillers can be found in many patents. For example, European Pat. Laid-Open Publication Nos. 66,672, 307,116, 456,142 and 779,325 (which are referred to as "first patent group" for convenience, hereinafter) disclose third materials, such as aliphatic acids, which are used, along with polyolefin and inorganic fillers, to make film smoother, or compositions with which the unbalance in physical properties between the machine direction and the transverse direction of a film can be solved. Leading to the first patent group, the third additives play an important role in mixing and dispersing a large quantity of inorganic fillers during extrusion and in producing uniform drawn films upon processing. Belonging to a second patent group, European Pat. Laid-Open Publication No. 232,060 discloses an after-treatment process, such as embossing, which can control the mechanical strength of air permeable films while U.S. Pat. No. 4,777,073 teaches a technique for increasing permeability and improving tear strength.

25 [0004] The prior arts of the first patent group are economically unfavorable due to the expensive third additives. In addition, they are poor in the compatibility with polyolefin, giving rise to a decrease in the tensile strength of the films. Further, after films are formed, the additives are released into the surfaces of the films during storage. Pertaining to after-treatment processes by which the physical properties of films can be controlled, the prior arts of the second patent group have a disadvantage of being limited in controlling physical properties of films as compared with the modification of film compositions.

30 [0005] The recent tendency has been directed to the productivity improvement of films in order to achieve high-speed film production. However, the compositions now commercially available are poor in processability because calcium carbonate is incorporated at an amount of as much as at least 50 % into polyolefin. To obtain desired permeability, calcium carbonate must be incorporated at an amount of more than 55 % or the films must be excessively drawn. Therefore, the conventional prior arts find difficulty in overcoming the unbalance in physical properties.

DISCLOSURE OF THE INVENTION

40 [0006] With the background in mind, the present invention has an object of providing a composition for an air-permeable film superior in processability and permeability.

[0007] It is another object of the present invention to provide a method for producing an air-permeable film using such a composition.

45 [0008] The present invention is characterized in that a variety of appropriate binder resins are employed to sufficiently express their own advantageous functions and to lower the content of the inorganic filler used. In this regard, a polyethylene resin with a wide molecular distribution is used to ameliorate processability when molding a film. A polypropylene resin is also used to control the softness, machine direction tensile strength, and thermal adhesiveness to propylene non-woven fabrics of a film. With the aim of improving the close adherence to a drawing roll upon drawing the film and of making it easy to conduct the interfacial separation from the inorganic filler, a polyolefin with a high melt index (MI) and an ethylene-propylene copolymer are contained in the composition. In cooperation, these polymers have advantages of assuring high permeability even at a low draw ratio, minimizing the unbalance in physical properties between the machine direction and the transverse direction of the drawn film, improving the tensile strength of the film, and preventing the physical property degradation due to the inorganic filler. Consequently, the air-permeable film is significantly improved in permeability and processability and has balanced physical properties between the machine direction and the transverse direction.

55 [0009] In accordance with one aspect of the present invention, there is provided a composition for an air-permeable film, comprising: 30 to 100 weight parts of a linear, low density polyethylene resin which ranges, in molecular weight distribution, from 7 to 20; 1 to 100 weight parts of a polypropylene resin; 1 to 30 weight parts of an ethylene-propylene copolymer; 5 to 30 weight parts of a polyolefin resin which has a melt index of 20 or higher; and 50 to 200 weight parts

of an inorganic filler based on 100 weight parts of the total resins.

[0010] In accordance with another aspect of the present invention, there is provided a method for producing an air-permeable film, in which a composition comprising 30 to 100 weight parts of a linear, low density polyethylene resin which ranges, in molecular weight distribution, from 7 to 20, 1 to 100 weight parts of a polypropylene resin, 1 to 30 weight parts of an ethylene-propylene copolymer, 5 to 30 weight parts of a polyolefin resin which has a melt index of 20 or higher, and 50 to 200 weight parts of an inorganic filler based on 100 weight parts of the total resins, is mono-axially drawn by 1.5 to 3 times, whereby the air-permeable film can be provided with superior processability and permeability.

BEST MODES FOR CARRYING OUT THE INVENTION

[0011] In the present invention, there is used a linear, low density polyethylene resin which has an MI of 0.5 to 5 g/10 min as measured according to ASTM D 1238, and a density of 0.915 to 0.935 with a molecular weight distribution ranging from 7 to 20. For example, a molecular weight distribution less than 7 causes an extrusion surging phenomenon when producing films at high speeds, making the film thickness poor in uniformity. On the other hand, when the molecular weight distribution exceeds 20, the physical properties of the film are degraded. The linear, low density polyethylene resin is used at an amount of 30 to 100 weight parts when a polypropylene resin is present at an amount of 1 to 100 weight parts, an ethylene-propylene copolymer at an amount of 1 to 30 weight parts, and a polyolefin resin which has a melt index of 20 or higher at an amount of 5 to 30 weight parts. For example, if the linear, low density polyethylene resin is used at an amount less than 30 weight parts, the film is poor in tensile strength and elongation. On the other hand, the use of the linear, low density polyethylene resin at an amount of more than 100 weight parts causes an extrusion surging phenomenon upon high-speed production.

[0012] With the aim of controlling the tensile strength and soft physical properties of a film, or ameliorating the thermal adhesiveness to a polypropylene non-woven fabric, a polypropylene resin is used at an amount of 1 to 100 weight parts when the linear, low density polyethylene resin is present at an amount of 30 to 100 weight parts. An amount less than 1 weight part does not show an addition effect. On the other hand, when using the polypropylene resin at an amount more than 100 weight parts, the soft sense of touch is depreciated. The polypropylene resin useful in the present invention has an MI of 1 to 10 and is selected from the group consisting of homo polypropylene, random polypropylene, impact polypropylene, and mixture thereof.

[0013] As for the ethylene-propylene copolymer used in the present invention, it functions to complement impact strength, transversely directional strength, and elongation in films as well as to improve the close adherence to a drawing role to give uniform drawing and high permeability. Useful is an ethylene-propylene copolymer which has an ethylene content of 60 to 80 % with a Mooney viscosity at 100 °C ranging from 10 to 30 when taking the fluidity of the resin into account. Preferable amounts of the ethylene-propylene copolymer are within the range of 1 to 30 weight parts. For example, an amount less than 1 weight part cannot obtain an addition effect while an amount exceeding 30 weight parts deleteriously affects the thermal resistance of the film.

[0014] To attain a film of high permeability, a polyolefin resin which has an MI of 20 g/10 min or greater as measured according to ASTM D 1238, and preferably 20 to 60 g/10 min, is used at an amount of 5 to 30 weight parts when the linear, low density polyethylene is added at an amount of 30 to 100 weight parts. The polyolefin useful in the present invention is selected from the group consisting of low density polyethylene, linear low density polyethylene, high density polyethylene, homo polypropylene, random polypropylene, impact polypropylene, and mixtures thereof.

[0015] As an inorganic filler, coated or un-coated calcium carbonate, barium sulfate or mixtures thereof are used. The inorganic filler is used at an amount of 50 to 200 weight parts based on 100 weight parts of the total resins, and preferably 80 to 150 weight parts. For instance, when the amount of the inorganic filler is below 50 weight parts as based on 100 weight parts of the resins, the film has poor permeability. On the other hand, an amount exceeding 200 weight parts brings about a decrease in the physical properties and processability of the film.

[0016] When the composition of the present invention is mono-axially drawn by 1.5 to 3 times, a film which is superior in tensile strength and has sufficient permeability can be obtained without being embossed with specific patterns.

[0017] A better understanding of the present invention may be obtained in light of the following examples which are set forth to illustrate, but are not to be construed to limit the present invention.

COMPARATIVE EXAMPLE I

[0018] A linear low density polyethylene for general casting (MI: 3.0, density: 0.919, Mw distribution: 5) was blended with calcium carbonate to give a permeable compound.

[0019] Into a twin extruder in which an extrusion temperature was maintained at 190 °C on average, 100 weight parts of the linear low density polyethylene were fed through a main inlet while 100 weight parts of stearic acid-coated calcium carbonate having an average particle size of approximately 1.5 µm were introduced through a side inlet. They

were melt-mixed, extruded and cut into pellets. Using a T-die film unit, the resulting compound was mono-axially drawn by 2 times to produce an air-permeable film 35 g/m² in balance weight. Its physical properties were measured and are given in Table 1, below.

COMPARATIVE EXAMPLE II

[0020] Using any resin having high melt index, permeable compound with high permeability was produced.

[0021] Into a twin extruder in which an extrusion temperature was maintained at 190 °C on average, 90 weight parts of the linear low density polyethylene and 10 weight parts of high density polyethylene having high melt index were mixed with an aid of a super mixer and then the mixture was fed through a main inlet while 100 weight parts of stearic acid-coated calcium carbonate having an average particle size of approximately 1.5 µm were introduced through a side inlet. They were melt-mixed, extruded and cut into pellets. Using a T-die film unit, the resulting compound was mono-axially drawn by 2 times to produce an air-permeable film 35 g/m² in balance weight. Its physical properties were measured and are given in Table 1, below.

EXAMPLES I TO III

[0022] A linear, low density polyethylene (MI: 3, density: 0.919, Mw distribution: 13) which was made wide in molecular distribution by use of two continuous stirring reactors, a random polypropylene (MI: 5.5, C₂ content: 2%), an ethylene-propylene copolymer (Mooney viscosity at 100 °C: 24, C₂ content: 74%, MI at 230 °C: 3.2), a high density polyethylene (MI: 20, density: 0.961), and an impact polypropylene (MI: 40) were mixed with the aid of a super mixer, as indicated in Table 1, below. Into a twin extruder, the resulting mixture was fed through a main inlet while 100 weight parts of stearic acid-coated calcium carbonate having an average particle size of approximately 1.5 µm in Examples I and III or 170 weight parts of barium sulfate having an average particle size of approximately 1.5 µm in Example II were fed through a side inlet, and the materials were melt-mixed, extruded and cut into pellets. Using a T-die film unit, the resulting compound was mono-axially drawn by 2 times to produce an air-permeable film 35 g/m² in balance weight. Its physical properties were measured and are given in Table 1, below.

TABLE 1

Materials & Properties	C. Example		Examples		
	I	II	I	II	III
LLDPE (MI=3, d=0.919, MWD=5)	100	90			
LLDPE (MI=3, d=0.919, MWD=13)			65	65	45
Random PP (MI=5.5, C ₂ =2%)			20	20	40
HDPE (MI=20, d=0.961)		10	10	10	
Impact PP (MI=40, C ₂ =6%)					10
Ethylene-Propylene copolymer (Mooney viscosity at 100°C =24, C ₂ =74%, MI at 230°C =3.2)			5	5	5
CaCO ₃	100	100	100		100
BaSO ₄				170	
Draw Ratio	2	2	2	2	2
Film Properties					
Max Film Production Speed (m/min)	35	50	85	80	75
Permeability (WVTR, g/m ² ·24hrs)	5300	9200	9900	9500	9700
Tensile Strength(g)	1450	1530	1720	1750	1850
MD (Machine direction)					
TD (Transverse direction)	600	570	580	560	570
Tensile Elong.(%)	170	160	160	170	150
MD (Machine direction)					
TD (Transverse direction)	490	460	470	480	420

[0023] The physical properties shown in Table 1, were measured as follows:

- Maximal Film Production Speed : Using a film machine which was used in practice, the maximal film production speed was 5 m/min before a thickness deviation owing to extrusion surging was observed by the naked eye.
- Permeability: according to ASTM E 96-92, a measurement was made of the change of permeability with weight gain after being stored for a certain period of time under a constant temperature and moisture.
- Tensile Strength and Tensile Elongation: according to KS-M3016, these were measured upon rupture in the machine direction and the transverse direction.

[0024] As apparent from the results of the above examples, the compositions for air-permeable films, according to the present invention, can be molded at an improved production speed into films which show high permeability at a low draw ratio, thereby minimizing the unbalance in physical properties between the machine direction and the transverse direction of the film. In addition, with an improvement in tensile strength, the film shows high permeability even at a low content of an inorganic filler, so that it can minimize the physical property degradation due to the inorganic filler.

[0025] The present invention has been described in an illustrative manner, and it is to be understood that the terminology used is intended to be in the nature of description rather than of limitation. Many modifications and variations of the present invention are possible in light of the above teachings. Therefore, it is to be understood that within the scope of the appended claims, the invention may be practiced otherwise than as specifically described.

Claims

1. A composition for an air-permeable film, comprising:

- 30 to 100 weight parts of a linear, low density polyethylene resin which ranges, in molecular weight distribution, from 7 to 20;
- 1 to 100 weight parts of a polypropylene resin;
- 1 to 30 weight parts of an ethylene-propylene copolymer;
- 5 to 30 weight parts of a polyolefin resin which has a melt index of 20 or higher; and
- 50 to 200 weight parts of an inorganic filler based on 100 weight parts of the total resins.

2. The composition as set forth in claim 1, wherein the linear, low density polyethylene resin has an melt index of 0.5 to 5 and a density of 0.915 to 0.935.

3. The composition as set forth in claim 1, wherein the polypropylene resin has a melt index of 1 to 10 and is selected from the group consisting of homo polypropylene, random polypropylene, impact polypropylene, and mixtures thereof.

4. The composition as set forth in claim 1, wherein the ethylene-propylene copolymer has an ethylene content of 60 to 80 % and a Mooney viscosity of 15 to 30 at 100 °C.

5. The composition as set forth in claim 1, wherein the polyolefin resin is selected from the group consisting of low density polyethylene, linear low density polyethylene, high density polyethylene, homo polypropylene, random polypropylene, impact polypropylene, and mixtures thereof.

6. The composition as set forth in claim 1, wherein the inorganic filler coated or un-coated carbon carbonate, coated or un-coated barium sulfate, or mixtures thereof.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 30 8650

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
Y	DATABASE WPI Section Ch, Week 199116 Derwent Publications Ltd., London, GB; Class A17, AN 1991-113325 XP002150367 & JP 03 053931 A (MITSUI TOATSU CHEM INC), 7 March 1991 (1991-03-07) * abstract *	1-6	C08J5/18 C08L23/10 C08L23/04 C08K3/00
Y	EP 0 565 938 A (NITTO DENKO CORP) 20 October 1993 (1993-10-20) * abstract; claims 1-14 * * column 5, line 8-24; examples 1,3 * * column 12, line 45 * * column 1, line 2 *	1-6	
Y	EP 0 841 376 A (TONEN SEKIYUKAGAKU KK) 13 May 1998 (1998-05-13) * abstract; claims 1-4 * * page 2, line 53-55 * * page 3, line 55 *	1-6	
A	GB 2 151 538 A (MITSUI TOATSU CHEMICALS) 24 July 1985 (1985-07-24) * abstract; claims 1-19 * * page 2, line 19 *	1-6	TECHNICAL FIELDS SEARCHED (Int.Cl.7) C08J C08L C08K
A	US 5 594 070 A (JACOBY PHILIP ET AL) 14 January 1997 (1997-01-14) * abstract; claims 1-6 * * column 1, line 25,26 * * column 4, line 34-55 * * column 6, line 12-55 * * column 7, line 55 *	1-6	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 19 October 2000	Examiner Bergmans, K
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03 82 (P04C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 30 8650

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	US 5 853 638 A (HAN YOUNG-KY00) 29 December 1998 (1998-12-29) * abstract; claims 1-6 * * column 3, line 63-66 * * column 4, line 1-21 * -----	6	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
The present search report has been drawn up for all claims			
Place of search		Date of completion of the search	Examiner
THE HAGUE		19 October 2000	Bergmans, K
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503/03-82 (10/04/01)

ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.

EP 99 30 8650

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

19-10-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 3053931 A	07-03-1991	NONE	
EP 0565938 A	20-10-1993	JP 5331306 A	14-12-1993
		DE 69304587 D	17-10-1996
		DE 69304587 T	23-01-1997
		US 5385777 A	31-01-1995
EP 0841376 A	13-05-1998	JP 10139958 A	26-05-1998
GB 2151538 A	24-07-1985	JP 60185803 A	21-09-1985
		JP 60199036 A	08-10-1985
		JP 1668123 C	29-05-1992
		JP 3033184 B	16-05-1991
		JP 60199037 A	08-10-1985
		JP 60129240 A	10-07-1985
		AU 551948 B	15-05-1986
		AU 3622184 A	20-06-1985
		CA 1245026 A	22-11-1988
		CA 1250724 A	07-03-1989
		CH 666222 A	15-07-1988
		DE 3445771 A	04-07-1985
		FR 2556648 A	21-06-1985
		IT 1179513 B	16-09-1987
		KR 8701966 B	23-10-1987
		NL 8403798 A, B,	16-07-1985
		NO 845047 A, B	17-06-1985
		NZ 210433 A	29-05-1987
		SE 465310 B	26-08-1991
		SE 8406114 A	17-06-1985
		US 4705812 A	10-11-1987
		US 4705813 A	10-11-1987
US 5594070 A	14-01-1997	US 5176953 A	05-01-1993
		AU 650072 B	09-06-1994
		CA 2056875 A	22-06-1992
		CN 1064491 A, B	16-09-1992
		DE 69131989 D	23-03-2000
		DE 69131989 T	05-10-2000
		EP 0492942 A	01-07-1992
		ES 2143462 T	16-05-2000
		JP 4309546 A	02-11-1992
		KR 212776 B	02-08-1999
		NZ 241070 A	23-12-1992
		US 5317035 A	31-05-1994
		US 5236963 A	17-08-1993
		AU 8838691 A	25-06-1992

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office. No. 12/82

ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.

EP 99 30 8650

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

19-10-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5853638 A	29-12-1998	NONE	

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office. No. 12/82